

Revised: December, 2009

### 100% SOLIDS EPOXY NOVOLAC COATING/LINING SYSTEM

TECHNI-PLUS EN 25.3 is an ambient cured epoxy novolac coating/lining system offering superior performance. TECHNI-PLUS EN 25 is a flake filled polymer system which is spray or roller applied in 25 mil coats to achieve film thicknesses from 25 to 50 mils depending upon service conditions.

TECHNI-PLUS EN 25.3 exhibits superior chemical resistance to aggressive, concentrated inorganic acids, dilute organic acids, alkalines, splash and spillage of organic solvents. In immersion service, TECHNI-PLUS EN 25.3 is applied in multiple coats over TECHNI-PLUS E 3 Primer and performs as a corrosion resistant immersion lining up to 140°F in severe environments such as chemical tank and process vessel linings. Depending on chemical environment, certain versions of TECHNI-PLUS EN 25 (e.g., post cured) are capable of higher temperatures in immersion. Consult with KCC on specific conditions. Dry temperature limit is 350°F. Successive improvements in TECHNI-PLUS EN 25 are designated by decimal point followed by sequence number, such as TECHNI-PLUS EN 25.3.

Also available in abrasion resistant version EN 25.3 AR; clear coat version, and roller version (EN 25.3 R) for

thinner applications of 10-15 mils per coat, or when broadcasting aggregate on horizontal concrete surfaces. Roller version is also sprayable. When used, clear coat version is applied at 5 to 10 mils topcoat over the flake filled, pigmented basecoat.

TECHNI-PLUS EN 25.3 is used on concrete and steel surfaces for chemical spill secondary containment. TECHNI-PLUS EN 25.3 possesses excellent abrasion and impact resistance and outstanding bond strength, and may be used in flooring protection applications. Depending on chemical conditions, TECHNI-PLUS EN 25.3 is applied in recommended thicknesses from 25 to 50 mils and will handle very aggressive chemicals, examples of which are shown below. As a result, TECHNI-PLUS EN 25.3 is a superior choice for trenches, sumps, containment dikes, tank linings, vaults, pipe tunnels, and process area surfaces.<sup>1</sup>

#### RESISTANCE TO WEATHERING

TECHNI-PLUS EN 25.3 is a high performance immersion lining/coating system. When used outdoors in ultraviolet light, some fading or change of color, and slight chalking could occur. These events will not have an adverse effect on the overall performance of coating system.

#### CHEMICAL RESISTANCE<sup>1</sup>

Examples of chemical resistance for immersion service are listed. Contact KCC Corrosion Control with complete operating service conditions for specific product recommendations.

ACIDS	ALKALINES	SOLVENTS, CHEMICALS
1-50% Acetic	1-25% Ammonium Hydroxide <sup>2</sup>	Acetaldehyde
Acid Plating Solutions	1%-saturated Barium Hydroxide	Acetone
1-25% Adipic	Black & Green Pulp Liquors	Acetonitrile, Acrylonitrile
1-30% Chromic	Cadmium Cyanide Plating	Cyclohexane
1-37% Hydrochloric	Copper Cyanide Plating	Ethyl & Butyl Acetate
1-40% Hydrofluoric	1-50% Potassium Hydroxide <sup>2</sup>	Formaldehyde
1-50% Nitric	1-15% Sodium Cyanide	Kerosene, Jet Fuel
Oleic	1-9% Sodium Hypochlorite	Methylene Chloride
1-85% Phosphoric	1-50% Sodium Hydroxide <sup>2</sup>	Methyl Ethyl Ketone
1-98% Sulfuric	1-30% Hydrogen Peroxide	1,1,1 Trichloroethane

**MAXIMUM SERVICE TEMPERATURE**<sup>1</sup> 350°F dry, 200°F for Splash/Spillage, 140°F for Immersion. EN 25.3R - this roller version is not typically used as a tank lining, especially at elevated temperatures. Consult KCC for Recommendation.

<sup>1</sup> FOR SPECIFIC RECOMMENDATIONS CONTACT KCC CORROSION CONTROL CO., LTD.

<sup>2</sup> TECHNI-PLUS EN 25 CLEAR COAT USED FOR HYDROFLUORIC ACID AND LOW CONCENTRATIONS OF HYDROXIDES.

<sup>3</sup> IF PROTECTED FROM DIRECT SUNLIGHT.

**TYPICAL PROPERTIES**

Solids Content:.....	100% Reactive
Volatile Organic Content: .....	Zero
Volume Mix Ratio: .....	2 parts Resin to 1 part Hardener (EN 25.3).
Flash Point: (Pensky Martens Closed Cup) .....	Resin.....> 250°F
	Hardener.....> 200°F
Viscosity: .....	5000 cps @ 77° (mixed).
Thinner:.....	<b>DO NOT THIN!</b>
Weight per Gallon:.....	9.4 lbs. + 0.2 (mixed).
Coverage for Steel: .....	(Theoretical)... 64 sq. ft. per gallon per coat when spray applied at 25 wet mils.
	(Practical) ..... 58 sq. ft. per gallon per coat when spray applied at 25 wet mils.
Coverage on Concrete:.....	Same as above if concrete is dense and primer is used. Porous or unprimed concrete may reduce coverage to 50 to 55 sq. ft. per gallon or less.
Color: .....	Tile Red, Beige (off white) and Medium Gray. Minimum quantities apply for special colors.

**PHYSICAL PROPERTIES OF CURED SYSTEM**

Compressive Strength (ASTM D-695): .....	22,500 psi
Tensile Strength (ASTM D-638): .....	9,650 psi
Bond Strength to Steel (ASTM D-1002): .....	2,250 psi
Bond Strength to Concrete (ASTM C-882): .....	> Tensile strength of concrete; breaks 5000 psi concrete.
Tensile Modulus (ASTM D-638): .....	475,000 psi
Impact Resistance (ASTM D-256, Method A): .....	0.15 ft-lb./in
Shore "D" Hardness (ASTM D-2240): .....	75
Abrasion Resistance (ASTM C C501-80): .....	EN 25.3: 52 mg loss/1000 cycles (1000 gms; CS-17 wheel).
	EN 25.3 AR: 30 mg loss/1000 cycles (1000 gms; CS-17 wheel).
Moisture Permeability (ASTM E 96-85): .....	0.0015 perm-inch

**POT LIFE/RECOAT TIME**

Temp.	Pot Life	Recoat Time	
		Minimum	Maximum
@ 25°F	180 min.	18 hrs.	2 days <sup>4</sup>
@ 50°F	90 min.	12 hrs.	2 days <sup>4</sup>
@ 75°F	30 min.	6 hrs.	2 days <sup>4</sup>
@ 90°F	15 min.	3 hrs.	2 days <sup>4</sup>

Pot life test on 200 gram sample; working time in larger quantities will be shorter! (See installation procedure sections.) For application of EN 25.3 at temperatures below 50°F contact KCC Corrosion Control for recommendations.

**PACKAGING**

TECHNI-PLUS EN 25.3 is packaged in pre-measured units as follows:

1 Gal. Unit	5 Gal. Unit	30 Gal. Unit
Resin 6.5 lbs.	Resin 32.3 lbs.	Resin 194 lbs.
Hardener 3.0 lbs.	Hardener 15.0 lbs.	Hardener 90 lbs.

(30 gallon units include multiple containers for hardener).

**BID SPECIFICATION**

Concrete or steel may be primed (optional) with a nominal 3 wet mils of TECHNI-PLUS E 3 Primer (required for surfaces to be scratch coated). Epoxy Scratch Coat shall be applied as needed to fill pits or "bug holes". TECHNI-PLUS EN 25.3 shall be applied at a nominal 25 to 50 mil thickness in coats of 25 wet mils. On horizontal traffic surfaces, 20 x 40 mesh dry round silica or 30 x 50 mesh flintshot shall be broadcast into the wet first coat until the surface appears dry, swept after cured, and topcoated with 15 to 20 wet mils of EN 25.3, depending on non-slip finish desired. The materials shall be applied to substrate prepared in accordance with the manufacturer's specifications.

**STORAGE AND SHELF LIFE**

TECHNI-PLUS EN 25.3 components should be stored in cool dry area and out of direct sunlight. The hardener is an **AMINE (KCC Red Label)** and **SHOULD NOT BE STORED NEAR PEROXIDES (KCC Yellow Label)**.

<sup>4</sup> IF PROTECTED FROM DIRECT SUNLIGHT.

**TYPICAL SHELF LIFE**

Temperature	Months
@ 50°F	12
@ 75°F	12
@ 80°-90°F	12

**INSTALLATION PROCEDURES**

The installation procedures in this bulletin will be as specific as possible.<sup>1</sup>

- **Equipment Design, Fabrication and Surface Preparation**

Whether the vessel is to be protected from the corrosive action of the contents or the contents are to be protected from contamination from the vessel surface, the coating must be continuous. The vessel design must consider the need to eliminate sharp corners, projections, crevices and acute angles and provide access to all surfaces. The design must also minimize movement when in operation.

**Steel**

External stiffeners and bracing should be used when acceptable. Internal bracing, dividers, nozzle projections and similar items must have continuous welds, (no skip welding) with weld rippling, undercutting and weld spatter ground smooth. Edges must be ground to a 1/8" radius. To facilitate the coating application, nozzles should have a larger diameter, (4" minimum) and short pipe nipple length. Nozzles smaller in diameter or with long pipe nipple lengths should be made of an alloy or utilize a Fiberglass Plastic nozzle insert. Threaded fittings must be avoided or made of alloy suitable to resist the corrosive contents.

All surfaces to be coated require a "White Metal" blast to SSPC-SP-5 or NACE 1, with an abrasive blast media that removes all visible mill scale, existing coating and rust. Performance is directly related to the anchor pattern profile and cleanliness of the steel. For immersion service conditions, highly corrosive environments and thermal shock, the steel substrate should be clean, dry and have a minimum anchor profile of 3 mils. For less severe conditions, nonimmersion service, splash, spillage and no thermal shock, a 2 mil anchor profile with a "Near White Metal" blast to SSPC-SP-10 or NACE 2, is acceptable.<sup>1</sup>

**Concrete**

All oil, grease, chemicals, polymeric materials and/or weak laitance should be removed by either mechanical or chemical methods. Mechanical methods such as

sandblasting, blasttracking or scarifying are the preferred methods. Chemical methods such as acid etching and detergents should be utilized to remove laitance, oil and grease when mechanical methods cannot be utilized. The concrete should have sufficient tensile strength (250 psi), and be clean and dry. All pits and surface imperfections, sharp corners, undercut areas from forms, honeycombing and bug holes opened up as a result of surface preparation must be filled with a scratch coat compatible with the coating system. It is the physical forcing, by troweling of a scratch coat onto and into the concrete surface that makes it possible to obtain an impervious finished coating. For specific scratch coat material recommendations, contact KCC Corrosion Control.

Specific recommendations and testing procedures for surface tensile strength and moisture content are contained in KCC Corrosion Control's Specification SC-01 "Preparation of Concrete for Thermoset Polymer Systems."

**Reference Documents:** *National Association of Corrosion Engineers* (NACE) Standard RP0178-89, "Fabrication Detail, Surface Finish Requirements, and Proper Design Considerations for Tanks and Vessels to be Lined for Immersion Service."

*Steel Structures Painting Council* (SSPC), Volume 1, Chapter 14.2, "The Lining of Steel Tanks."

- **Mixing and Application**

**DO NOT ATTEMPT COATING APPLICATION IF SUBSTRATE TEMPERATURE IS WITHIN 5°F OF DEW POINT OR IF RELATIVE HUMIDITY IS GREATER THAN 95%.**

If coating concrete surfaces, concrete expels air during the day and intakes air during the night. The best time to apply coating is late afternoon or early evening at which time concrete is least likely to expel air. Other precautions such as shading the work area from sunlight to minimize the heating of the substrate and elimination of cyclic temperature changes will also reduce expulsion of air. Use of primer is optional, although it may minimize air expulsion from concrete. The resin component should be stirred with mechanical mixer thoroughly prior to adding TECHNI-PLUS EN 25 Hardener. Add hardener to resin portion and mix using mechanical mixer approximately 2 minutes. **DO NOT THIN!** If plural component spray equipment is used, resin component must be thoroughly stirred. Hardener is not added to resin, but mixed in spray equipment at nozzle. Proper ratio is important to ultimate cure and film properties.

<sup>1</sup> FOR SPECIFIC RECOMMENDATIONS CONTACT KCC CORROSION CONTROL CO., LTD.

TECHNI-PLUS EN 25 is designed to be applied by spray, brush or roller. Roller or brush application is especially good for small areas and spot repair. When spraying, the pots and lines should be flushed with KCC's 622 clean up solvent after every 3 to 4 batches when temperatures exceed 80°F. TECHNI-PLUS EN 25 is applied at a nominal 25 to 50 mil thickness in coats of 25 wet mils. On horizontal traffic surfaces, 20 x 40 mesh dry round silica or 30 x 50 mesh flintshot may be broadcast into the wet first coat until the surface appears dry, swept after cured, and topcoated with 15 to 20 wet mils of TECHNI-PLUS EN 25, depending on non-slip finish desired.

**APPLICATION METHODS**

Brush-Roller: Natural bristle brush short nap wool or mohair roller.

Spray: Refer to KCC Recommended Practice Bulletin RP-01, Spray Application Methods and Equipment. Note limited pot life if spraying.

• **Pot Life** (See values on Page 2)

The pot life or working time of the material is mass sensitive, the larger the volume the shorter the pot life. Do not catalyze more material than can be used within the pot life. Above 90°F ambient temperature, best results are obtained when the catalyzed material is poured into

**CURE TIME**

The cure time is dependent on temperature of the substrate. The ambient air temperature may not be the temperature of the substrate, i.e. direct sunlight will heat substrate to higher temperature than ambient air. In winter, substrate may be colder than ambient air. The substrate temperature should be measured and dew point calculated prior to coating. Substrate temperatures below 50°F will retard curing.

**Time to Complete Cure**

If substrate is maintained:	@ 50°F.....	96 hrs.
	@ 75°F.....	48 hrs.
	@ 90°F.....	24 hrs.

**INSPECTION OF FILM INTEGRITY**

During installation of the coating, care should be taken to provide for the correct specified uniform thickness of material by carefully checking at regular, pre-specified intervals, with a wet film thickness gauge.

After allowing adequate cure time based on the actual substrate temperature, the surface should be inspected for runs, sags, foreign matter and under cured areas caused by insufficient hardener quantity, incomplete mixing or low temperature. If under cured areas are found, they must be repaired.

smaller containers reducing the mass. When ambient temperature exceeds 80°F the pot life can be extended by cooling the materials. The materials should be stored between 65°F and 75°F for 24 hours prior to use for optimum handling properties. If plural component application equipment is used, materials are not premixed and pot life is not a factor. Mixing chamber and spray tip must be kept clean and flushed with KCC's 622 clean up solvent.

• **Clean-Up**

All mixing equipment, spray equipment and brushes should be cleaned immediately after use. Solvents recommended for clean-up are KCC's 622 Clean-up Solvent or methyl ethyl ketone.

**RECOAT AND TOPCOAT LIMITATIONS**

The maximum recoat time for all KCC products exposed to direct sunlight (ultraviolet light) is 2 days. This time period can be extended to 7 days by protecting the product from exposure to direct sunlight. In the event that either of above recoat times are expired, the surface must then be roughened or abraded by light abrasive blasting to remove all shiny surfaces of the product, and then, after wiping all dust from the surface, the product is ready for topcoat application, within 4-6 hours.

Film thickness on steel structures should be checked with a magnetic dry film thickness gauge. Coatings to be subjected to immersion service should be tested for minute discontinuities (pin holes) using a high voltage DC holiday detector, set at no more than 100 volts per mil of the film thickness being tested.

Coatings on concrete surfaces may be checked for continuity by spark testing if so desired. If a coating is to be spark tested, a conductive primer must be used on the concrete (E 3 C) in place of the standard primer, TECHNI-PLUS E 3. Follow test procedure for completed coating outlined above.

**Reference Documents:** *Steel Structures Painting Council* (SSPC), Volume 1, Chapter 14.2, "The Lining of Steel Tanks", Section VIII, Inspection.

*National Association of Corrosion Engineers* (NACE), Standard RP0188-88, "Discontinuity (Holiday) Testing of Protective Coatings" and Standard RP0288-88, "Inspection of Linings on Steel and Concrete."

### **SAFETY**

**CAUTION: Exposure of this product to concentrated nitric acid, above 70% concentration, is not recommended, as a nitration reaction may result, with potential hazard of fire or explosion. This does not mean the product is recommended for concentrations of nitric acid up to 70%.<sup>1</sup>**

TECHNI-PLUS EN 25 Resin contains epoxy resins. EN 25 Hardener contains *AMINES* (KCC Red Label) and **SHOULD NOT BE STORED NEAR PEROXIDES** (KCC Yellow Label).

### **WARRANTY**

For product warranty see KCC Corrosion Control Co., Ltd. **STANDARD TERMS AND CONDITIONS** (U. S. 3/2006 KCC-Sale), **stated terms including limitation of liability constitute the total warranty.**

**The information contained in this bulletin is believed to be accurate and reliable but is not to be construed as implying any warranty or guarantee of performance. The suggestions or recommendations of data contained in this bulletin are made without guarantee or representation as to results. We suggest that the user evaluate these suggestions or recommendations in your facility, laboratory or in field testing prior to use. For specific KCC Corrosion Control Co., Ltd. product Limited Warranty and Limitations of Liability see KCC Corrosion Control Co., Ltd. Terms and Conditions of Sale – U.S. 3/2006 KCC-Sale. No statement contained herein shall infer or be construed as granting the right or permission to use, in any manner whatsoever, any patent or other intellectual property owned by any KCC company or any KCC affiliate company.**

---

### **NOTES:**

All components should be stored in a cool dry place out of direct sunlight. When working with any polymers, hardeners and dry aggregate fillers always wear appropriate safety glasses, breathing protection, and gloves.

Any contaminated clothing should be washed prior to being reworn. The vapors given off during application and cure should not be allowed to build up. The ventilation should be sufficient to turn over the air with special consideration for enclosed area. When using these types of materials any sources of ignition should be eliminated within a 50 ft. range.

**Material Safety Data Sheets** have been supplied with your shipment. KCC Corrosion Control recommends that the personnel applying the materials read and understand these, as well as product labels, prior to mixing any material. If the resin or hardener are splashed in the eyes flush with clean water for 15 minutes and **CONTACT A PHYSICIAN. IF INGESTED DO NOT INDUCE VOMITING AND CONTACT A PHYSICIAN.**

All empty containers; bags, cans, bottles and excess material must be properly disposed of in accordance with applicable Federal, State and Local Codes. **IN EMERGENCY SITUATIONS CONTACT CHEMTREC AT 800/424-9300.**